



**SC-36 Fast Stain**

**Description**

Westcoat SC-36 Fast Stain is a solvent soluble, deep penetrating, fast drying, drop in powder stain. When used with acetone this dye dries to touch in just seconds, and produces colors from earth tones to vibrant colors on concrete and cementitious overlays.

**Uses**

When mixed with acetone SC-36 can be used as a primary coloring system. SC-36 may be used in conjunction with Acid and Waterbased stains as a secondary coloring system.

**Advantages**

- Fast drying
- Deep penetrating
- Colors can be blended for unlimited color selection
- Safe to ship UPS
- Great Interior color fastness

- Easy to use
- Can be sealed with both solvent and water-based sealers
- No rinsing needed

**Colors**

- |              |             |
|--------------|-------------|
| Black        | Brown       |
| Burnt Orange | Blue        |
| Dark Brown   | Light Brown |
| Light Green  | Navy        |
| Purple       | Red         |
| Turquoise    | Yellow      |

**Packaging**

- 18 Grams 1/2 pint can (For 1 gallon acetone)
- 90 Grams 1 pint can (For in 5 gallons acetone)

**INSPECTION / PREPARATION**

**Inspection**

Surface must be structurally sound. The surface must be dry and free of oil, grease, curing agents, dirt, dust, or other foreign material. The concrete should be at least 2500 psi and cured a minimum of 28 days. Before starting flooring work, test existing concrete slab for efflorescence, moisture and hydrostatic pressure.

**Preparation**

Methods of preparation may vary according to the desired outcome. Factors include the forecasted use of the surface, the environment in which it is to be installed, and if a sealer will be used. When preparing the surface take in to consideration the desired final look and prep accordingly

**APPLICATION**

**Mixing**

For ease of mixing begin by adding a small amount of acetone into the SC-36 Fast Stain powder container. Pour approximately 6 ounces of acetone into the half pint container of pre-measured Fast Stain powder (1 gallon mix) or 12 ounces of acetone into the pint container of pre-measured Fast Stain powder (5 gallon mix). Replace the lid and shake to dissolve the powder. Once powder has dissolved, place a funnel in the opening of the 1 or 5 gallon acetone and pour contents of first mix into remaining acetone. Shake entire mixture and let sit for 15 minutes, shake again and the Fast Stain is now ready to apply. Colors may be varied by adding more or less acetone.

**Applying Product**

Material may be applied with a solvent safe sprayer, material can also be brushed or broomed. Additional coats may be applied after first coat has dried for 10 to 20 minutes. Additional coats will produce a darker color. Multiple colors may be layered or sprayed at the same time to create a variegated finish. Be sure to paper off any areas that you do not want dyed. If used in a floor polishing system, apply the acetone dye prior to the final polishing processes.

**Coverage**

The coverage will vary depending on the surface. Up to 400 sq ft per gallon on a smooth surface and between 150-250 on rough surfaces.

Be sure to extinguish all pilot lights and sources of ignition, ventilate the area prior to starting the job. Acetone fumes are extremely flammable.

**Clean Up**

If cured, material can only be removed mechanically or with an environmentally-safe solvent.

---

## LIMITATIONS

- Concrete must be free of sealers, wax, or curing agents.
- Apply in thin coats.
- Will not hide imperfections or stains in concrete.
- Product will stain concrete and produce a mottled look.
- Colors and effects will vary.
- Read Product Specification Sheets for every product you will be using before beginning the project.
- Stains are translucent and somewhat transparent
- **CAUTION** when mixed with acetone product is **EXTREMELY FLAMABLE**.

---

## HEALTH PRECAUTIONS

Inhalation of vapor or powder can cause headache, nausea, irritation of nose, throat, and lungs. Prolonged or repeated skin contact can cause slight skin irritation.

---

## DISCLAIMER

PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.



**westcoat**<sup>™</sup>

770 Gateway Center Drive San Diego, CA 92102  
800•250•4519 • Fax 619•262•8606 • westcoat.com