



TC

TEXTURE COAT
DECORATIVE TEXTURED SURFACES

TC-40 Liquid Colorant

Description

Westcoat TC-40 Liquid Colorant is an iron oxide slurry formulated with high pigment levels of 60-70%.

Uses

TC-40 is designed to tint Westcoat cement to a variety of colors. TC-40 may also be used with most other portland cement-based products, such as stucco or concrete.

Advantages

- Fade Resistant
- Mixes Easily
- Convenient Packaging
- ASTM 979 Compliant
- Choice of Colors

Packaging

TC-40-Liquid Colorant 10 oz bottles.

INSPECTION / PREPARATION

Inspection

Concrete must have 1/4 inch slope per linear foot with a rough broom finish (like 60 to 80 grit sand paper) and be open and porous. Allow concrete a minimum 28 days and make sure that the moisture content at 4% or less. Plywood must be at least 5/8 inch CDX exterior grade. Slope must be a minimum of 1/4 inch per linear foot. Decks should meet local building code. The deck should be tongue and groove and properly blocked and screwed into place.

Preparation

On concrete remove all coatings to a sound concrete base. Prepare surface by grinding, water blasting or shot blasting to achieve surface that feels like 50 to 80 grit sand paper. On plywood be sure the surface is clean, dry and free of grease, paint, oil, dust or any foreign material that may prevent proper adhesion.

APPLICATION

Applying Product

After cement mix is blended with water and/or acrylic, carefully measure the desired amount of colorant using a small measuring cup or an oral syringe. The typical amount is 1-4 ounces per 50 pound bag of cement, not to exceed 10 ounces.

Pour the colorant into the mix and blend with a mechanical mixer at 300-500 rpm. Make sure to rinse all the colorant from your measuring cup with water.

Note: You may also add the colorant to the water and/or acrylic before combining with the Westcoat cements or chosen stucco, concrete, or mortar mix.

Clean Up

Uncured material can be removed with soap and water.

LIMITATIONS

- This product is designed for professional use only.
- It is strongly recommended that a sample be approved by the customer before starting the application.
- Westcoat assumes no responsibility for color variations after placement of material.
- Read individual information sheets for each Westcoat

- product you will be using before beginning project.
- Moisture will effect the color of uncured colored cements.
- Do not apply in temperatures below 55° or above 95°. Cooler temperatures will cause slower drying times
- Do not allow any Westcoat products to FREEZE.

HEALTH PRECAUTIONS

Inhalation of vapor or mist can cause headache, nausea, irritation of nose, throat, and lungs. Prolonged or repeated skin contact can cause slight skin irritation.

DISCLAIMER

PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST THE MANUFACTURER OF WESTCOAT, SHALL BE LIMITED SOLELY TO THE REPLACEMENT OF ANY DEFECTIVE MATERIAL OR A PAYMENT BY THE MANUFACTURER IN AN AMOUNT EQUAL TO THE COST OF THE ORIGINAL MATERIAL.

TECHNICAL DATA

| Sample Name | Cemant Used | Colorant Used | Water:Accent Powder Ratio |
|--------------|---------------------------------|---------------|---|
| Antique Blue | TC-2 White Textured Cement | ¼ oz Smoke | 10 to 1 Slate Blue |
| Flintstone | TC-5 Light Gray Textured Cement | None | 4 to 1 Sand |
| Suede | TC-2 White Textured Cement | ¼ oz Cinnamon | 8 to 1 Spanish Brown |
| Red Rock | TC-2 White Textured Cement | 4 oz Peach | 8 to 1 Spanish Brown |
| Tornado | TC-2 White Texture Cement | ¼ oz Smoke | 10 to 1 Pewter Gray |
| Sage | TC-5 Light Gray Texture Cement | None | 8 to 1 Slate Green |
| Arroyo | TC-2 White Texture Cement | ¼ oz Cinnamon | 4 to 1 Sand |
| Auburn | TC-2 White Texture Cement | 1 oz Cinnamon | 4 to 1 Mission Red |
| Charcoal | TC-2 White Texture Cement | 1 oz Smoke | 6 to 1 Black |
| Smoke Stone | TC-2 White Texture Cement | ¼ oz Straw | 4 to 1 Pewter Gray |
| Russet | TC-2 White Texture Cement | ¼ oz Cinnamon | 8 to 1 Terra Cotta |
| Aztec | TC-2 White Texture Cement | 4 oz Peach | 4 to 1 Tile Red |
| Ash | TC-2 White Texture Cement | ¼ oz Smoke | Slate Green and Slate Blue Dry Rub |
| Egypt | TC-2 White Texture Cement | ¼ oz Yellow | 1 part Slate Blue to 2 parts Travatan Dry Rub |
| Milan | TC-2 White Texture Cement | ½ oz Green | 1 part Black to 4 parts Travatan Dry Rub |
| Moccasin | TC-2 White Texture Cement | ¼ oz Smoke | Sand, Black, and Mission Red Dry Rub |



westcoat[™]

770 Gateway Center Drive San Diego, CA 92102
800•250•4519 • Fax 619•262•8606 • westcoat.com